

Specification Sheet Z-Perform 2000D

Features:

- Direct thermal, smooth, paper label with an all-temp permanent acrylic adhesive
- Recommended for printing applications up to 8 inches per second
- Topcoating is suitable for fanfolding
- Meets FDA 175.105 for indirect food contact requirements
- Does not contain natural rubber latex
- Available in white (65791RM)

Suggested Applications:

- Packaging and compliance labeling
- Indoor labeling applications
- Work in process labeling
- Food labeling

Material Construction:

| | Description | | Caliper |
|-----------|-----------------------------------|-------|-----------------|
| Facestock | White smooth topcoated paper | | 3.0 mil |
| Adhesive | All-temp, acrylic-based | | 0.8 mil |
| Liner | 40 lb. semi-bleached, kraft stock | | 2.3 mil |
| | | Total | 6.3 mil +/- 10% |

Temperature Performance:

Minimum Application Temperature: -40° F (-40° C)

Service Temperature: -65° F to 131° F (-54° C to 55° C)

Storage Conditions:
32° F to 70° F (0° C to 21° C) at 35% to 50% RH

Expected Exterior Life
Not recommended for outdoor use

Applications with Chemicals

| | Weak | | | | Moderate | | | Harsh | | | Extreme | | | | | | |
|----|-------|------------|------------|-------|-------------------|---------|---------|--------|-----|----------|---------|-----|---------|-----------|-----|-----|--------|
| | Blood | Body Fluid | Salt Water | Water | Window Cleaner | Alcohol | Ammonia | Bleach | IPA | Gasoline | Grease | Oil | Acetone | IR Reflow | MEK | TCE | Xylene |
| DT | | | Χ | Χ | X | | | | | | | | | | | | |

180º Peel Room Temperature Peel Adhesion (oz/in):

| Corrugate | | Ste | eel | Polyca | rbonate | Polyethylene | | | |
|-----------|-------|-------|-------|--------|---------|--------------|-------|--|--|
| 5 min | 24 hr | 5 min | 24 hr | 5 min | 24 hr | 5 min | 24 hr | | |
| 17 | 18 | 49 | * | 57 | * | 26 | 46 | | |

^{*}Attraction between adhesive and surface is so great that the facestock rips.

NOTE: For guidance only, not to be used for setting specifications

Product Performance and Suitability

The information contained in this document is to be used for guidance only and is not intended for use in setting specifications. All purchasers of Zebra products shall be solely responsible for independently determining if the product conforms to all requirements of their unique application.