



# Specification Sheet

## Z-Xtreme 4000T

### Features:

- Thermal transfer, matte polyester label with a high-performance permanent acrylic adhesive
- Good smear/scratch resistance
- Excellent durability and chemical resistance
- Topcoating is suitable for fanfolding
- Available in white (05381RM) and silver (05385RM)

### Suggested Applications:

- UL/CSA compliance product labeling
- Top-side PCB labeling
- Asset labeling
- Automotive labeling
- Serial plate labeling

### Material Construction:

	Description	Caliper
Facestock	White or silver matte coated polyester	2.0 mil
Adhesive	Permanent, acrylic-based	1.0 mil
Liner	50 lb. semi-bleached, kraft stock	3.0 mil
<b>Total</b>		<b>6.0 mil +/- 10%</b>

### Temperature Performance:

- Minimum Application Temperature: 50° F (10° C)
- Service Temperature: -40° F to 300° F (-40° C to 149° C)
- Storage Conditions: 32° F to 70° F (0° C to 21° C) at 35% to 50% RH
- Expected Exterior Life 3 years



## Suggested Ribbons for Applications with Chemicals

	Weak					Moderate				Harsh			Extreme				
	Blood	Body Fluid	Salt Water	Water	Window Cleaner	Alcohol	Ammonia	Bleach	IPA	Gasoline	Grease	Oil	Acetone	IR Reflow	MEK	TCE	Xylene
<b>5555</b>	X	X	X	X	X	X	X	X	X		X	X					
<b>3200</b>	X	X	X	X	X	X	X	X	X	X	X	X	X		X	X	X
<b>5586</b>	X	X	X	X	X	X	X	X	X	X	X	X	X		X	X	
<b>5095</b>	X	X	X	X	X	X	X	X	X		X	X					

### UL/CSA Acceptances:

Z-Xtreme 4000T White and Silver with 5319, 5049, 5555, 3200, 5586, 5095 and 5100 ribbons is UL-recognized and CSA-accepted for indoor/outdoor use.

### 180° Peel Room Temperature Peel Adhesion (oz/in):

Steel		Polycarbonate		Polyethylene	
5 min	24 hr	5 min	24 hr	5 min	24 hr
40	52	47	75	25	29

### Facestock Tensile Strength:

- Machine direction: 18,000 psi
- Transverse direction: 22,000 psi

NOTE: For guidance only, not to be used for setting specifications

### Product Performance and Suitability

The information contained in this document is to be used for guidance only and is not intended for use in setting specifications. All purchasers of Zebra products shall be solely responsible for independently determining if the product conforms to all requirements of their unique application.

